

## RULLGARDIN & LAMELL FILMER

Filmtyp	UV- transmission	Visible Light Transmission	Total Solar Energy Rejected	Glare Reduction	Solar Reflection	Solar Absorption	Solar Transmission	g Value (Solar heat gain coef.)
Slät filmer								
Mirage	1%	13%	56%	86%	15%	59%	26%	0,41
Präglade filmer								
Quartz	1%	20%	78%	80%	65%	20%	15%	0,2
Bronze	1%	9%	83%	90%	62%	28%	10%	0,27
Baltic	1%	9%	82%	91%	60%	30%	10%	0,27
Luxor	1%	8%	88%	90%	71%	23%	6%	0,19
Emeraude	1%	14%	80%	84%	62%	25%	13%	0,25
Saphir	1%	12%	80%	86%	60%	27%	13%	0,28
Eclipse	1%	3%	92%	97%	77%	19%	4%	0,17
Cobalt	1%	3%	92%	97%	78%	19%	3%	0,17
Mirror	1%	3%	94%	97%	82%	16%	2%	0,14
Onyx (black out)	1%	0%	95%	100%	83%	17%	0%	0,14
Select	1%	3%	86%	97%	53%	43%	4%	0,29
Alustar	1%	3%	92%	97%	78%	19%	3%	0,17
Metalliserad tyg film								
Soltis white	NC	10%	83%	90%	41%	46%	13%	0,41
Energy white	NC	8%	±80%	92%	56%	36%	8%	0,33
Designo white	NC	8%	±80%	92%	56%	36%	8%	0,33
Blackout white	NC	0%	90%	100%	65%	35%	0%	0,30

### Solfilmsmontören Sverige AB

Porfyrgatan 12  
254 68 Helsingborg

042-165010

www.solfilm.se  
info@solfilm.se