

UTVÄNDIGA SOLSKYDDSFILMER

Filmtyp	UV transmission	Visible light transmission	Reflection of external visible light	Reflection of internal visible light	Total solar energy rejected	Total solar energy rejected *	Solar energy reflection	Solar energy absorption	Solar energy transmission	Reduction in Solar Glare	g-value	u-value	Shading coefficient	PET/PVC composition	Thickness
Solskyddsfilm															
Bronze 80XC	1%	11%	18%	60%	80%	85%	34%	57%	9%	90%	0,23	5,1	0,2	PET	50 µ
Chrome 245 XC	<1%	59%	17%	17%	53%	57%	25%	32%	43%	40%	0,5	5,8	0,4	PET	60 µ
Chrome 270XC	<1%	30%	43%	43%	71%	74%	53%	26%	21%	69%	0,29	5,8	0,3	PET	60 µ
Chrome 285XC	<1%	16%	65%	65%	84%	90%	66%	23%	11%	85%	0,14	5,8	0,1	PET	60 µ
Clarity 245XC	<1%	59%	17%	17%	53%	57%	25%	32%	43%	40%	0,5	5,8	0,4	PET	65 µ
Copper 80XC	1%	20%	37%	37%	78%	84%	39%	46%	15%	79%	0,27	-	0,2	PET	75 µ
Master 80XC	1%	16%	62%	60%	89%	89%	67%	20%	13%	84%	0,18	5,1	0,2	PET	60 µ
Natural 260XC	<1%	40%	16%	16%	59%	63%	19%	48%	33%	61%	0,4	5,8	0,4	PET	75 µ
Natural 275XC	<1%	20%	31%	18%	70%	73%	24%	57%	19%	80%	0,29	5,8	0,3	PET	75 µ
Nickel 50XC	1%	47%	20%	20%	50%	53%	19%	40%	41%	52%	0,49	5,7	0,5	PET	50 µ
Nickel 80XC	1%	20%	37%	16%	74%	77%	41%	43%	16%	78%	0,28	5,64	0,3	PET	60 µ
Sky Black 99XC	1%	<1%	88%	11%	99%	99%	85%	14%	1%	100%	0,03	5,1	0,2	PET	100 µ
Sky White 99XC	1%	<1%	88%	11%	99%	99%	85%	14%	1%	100%	0,03	5,1	0,2	PET	100 µ
Spectra 22XC	<1%	78%	9%	9%	45%	48%	10%	46%	44%	18%	0,55	5,08	0,6	PET	60 µ
Spectra 33XC	<1%	68%	9%	9%	52%	56%	8%	54%	38%	29%	0,49	5,08	0,6	PET	50 µ
Spectra 44XC	<1%	54%	14%	14%	57%	61%	10%	62%	28%	42%	0,42	5,08	0,5	PET	60 µ
Vista 90XC	1%	10%	64%	12%	82%	86%	61%	31%	8%	90%	0,17	5,1	0,2	PET	60 µ
Vista 99XC	1%	1%	88%	11%	99%	99%	85%	14%	1%	100%	0,03	5,1	0,2	PET	75 µ

(*on double glazing 4-16-4)