

## SÄKERHETSFILMER

Filmtyyp	UV transmission	Visible light transmission	Reflection of external visible light	Reflection of internal visible light	Total solar energy rejected	Total solar energy rejected *	Solar energy reflection	Solar energy absorption	Solar energy transmission	Reduction in Solar Glare	g-value	u-value	Shading coefficient	PET/PVC composition	Thickness
<b>Invändig säkerhetsfilm</b>															
Super Clear 3C	<1%	93%	7%	4%	16%	17%	9%	8%	83%	-	-	5,7	0,9	PET	90 µ
Super Clear 4C	5%	90%	7%	4%	16%	17%	9%	8%	83%	8%	0,83	5,7	0,9	PET	125 µ
Super Clear 7C	5%	85%	11%	11%	20%	21%	10%	8%	82%	15%	0,83	5,7	0,9	PET	210 µ
Clear 8C	5%	83%	10%	10%	20%	21%	10%	14%	76%	15%	0,82	5,7	0,9	PET	240 µ
Clear 12C	5%	82%	12%	12%	20%	21%	10%	9%	81%	16%	0,80	5,7	0,9	PET	310 µ
Clear 18C	5%	80%	12%	12%	20%	21%	10%	9%	81%	16%	0,80	5,7	0,9	PET	520 µ
<b>Utvändig säkerhetsfilm</b>															
Safe 4XC	5%	85%	11%	11%	19%	19%	9%	14%	77%	14%	0,83	5,7	0,9	PET	120 µ
Clear 4XC G	1%	93%	9%	9%	17%	18%	10%	8%	82%	14%	0,83	5,7	0,9	PET	125 µ
Clear 8XC	1%	83%	10%	10%	20%	21%	10%	14%	76%	15%	0,82	5,7	0,9	PET	240 µ
<b>Anti Graffiti</b>															
Protec 4C	2%	85%	11%	11%	19%	19%	9%	14%	77%	14%	0,83	5,7	0,9	PET	120 µ
Protec 6C	5%	86%	11%	11%	20%	20%	10%	8%	83%	14%	0,83	5,7	0,9	PET	180 µ
Clear 4XC G	1%	93%	9%	9%	17%	18%	10%	8%	82%	14%	0,83	5,7	0,9	PET	125 µ
<b>Mirror</b>															
Secur 4	5%	85%	11%	11%	19%	20%	9%	14%	77%	14%	0,83	5,7	0,9	PET	125 µ
<b>Anti-Fog</b>															
Clear AB	1%	87%	11%	11%	18%	18%	10%	14%	76%	14%	-	-	-	PET	60 µ

(\*on double glazing 4-16-4)