



CLEAR 18 C

Clear 18 C films help secure your windows by ensuring that the glass does not shatter, remaining transparent and retaining its overall integrity in the event of an impact, explosion or fire. Ideal for use on large glazed surfaces, these films are European Standard EN 356 compliant.



Storage from -5°C to +40°C
3 YEARS



European Standard EN 356
P2A



REACH RoHS compliant
RESPECTED

TECHNICAL DATA

Data calculated based on film applied to clear glass 3 mm thick (* on double glazing 4-16-4)

Ultraviolet transmission	5%
Visible light transmission	80%
Reflection of external visible light	12%
Reflection of internal visible light	12%
Total solar energy rejected	20%
Total solar energy rejected 2 *	21%
Solar ratio:	
Solar energy reflection	10%
Solar energy absorption	9%
Solar energy transmission	81%
Reduction in Solar Glare	16%
g-value	0.80
u-value	5.7
Heat loss Reduction (Winter)	0
Shading coefficient	0.9
Tensile strength (kg/cm ²)	85
Elongation at break	119%
Installation type	Interior
Roll length	30,5 m
Film composition	PET
Thickness	520 µ
Colour from the outside	Transparent

MAINTENANCE

Use soapy water solution for cleaning. Do not clean for at least a month after installation and do not apply any type of stickers or adhesive on the film. For more information read our maintenance instructions and quality standards on our website, www.solfilm.se

INSTALLATION ADVICE

Vertical installation and on standard glass surface *

Clear single pane	✓
Tinted single pane	✓
Reflective tinted single pane	✓
Clear double pane	✓
Tinted double pane	✓
Reflective tinted double pane	✓
Gas-filled double pane - Low E	✓
STADIP EXT. clear double pane	✓
STADIP INT. clear double pane	✓

✓ Yes ! Caution ✗ Not

Recommended

* Recommendations provided on the basis of a glazed surface covering up to 2.5 m².

CONSTRUCTION

1. Hard scratch resistant layer, for durability and ease of maintenance during window cleaning
2. High optical quality polyester 150 µ
3. Bonding adhesive
4. High optical quality polyester 150 µ
5. Bonding adhesive
6. High optical quality polyester 150 µ
7. Reinforced PS Adhesive to accompany the elasticity of the film in case of impact, glass polymerization within 30 days
8. Protection release liner, disposable after installation

