

INVÄNDIGA SOLSKYDDSFILMER

Filmtyper	UV transmission	Visible light transmission	Reflection of external visible light	Reflection of internal visible light	Total solar energy rejected	Total solar energy rejected *	Solar energy reflection	Solar energy absorption	Solar energy transmission	Reduction in Solar Glare	g-value	u-value	Shading coefficient	PET/PVC composition	Thickness
Solskyddsfilmer															
Blue 80 C	1%	12%	18%	63%	72%	68%	35%	47%	18%	86%	0,27	5,13	0,3	PET	50 µ
Bronze 80 C	1%	12%	18%	55%	76%	72%	34%	57%	9%	91%	0,23	5,1	0,2	PET	50 µ
Cobalt 80 C	1%	10%	18%	60%	76%	72%	33%	59%	59%	90%	0,23	5,1	0,2	PET	50 µ
Copper 50 C	1%	50%	17%	17%	55%	50%	22%	43%	35%	50%	0,46	5,39	0,5	PET	60 µ
Copper 65 C	1%	35%	26%	26%	65%	60%	39%	36%	25%	63%	0,34	5,23	0,39	PET	60 µ
Copper 80 C	1%	20%	36%	36%	77%	72%	45%	42%	13%	79%	0,22	5,1	0,2	PET	60 µ
Gold 80 C	1%	15%	50%	64%	78%	75%	50%	38%	8%	83%	0,25	5,1	0,28	PET	50 µ
Green 80 C	1%	15%	36%	63%	77%	73%	36%	55%	9%	85%	0,23	5,1	0,2	PET	50 µ
Multiglass 66 C	1%	47%	29%	28%	66%	63%	47%	25%	28%	52%	0,36	4,9	0,4	PET	55 µ
Silver 50 C	1%	59%	26%	26%	58%	54%	31%	29%	40%	47%	0,45	5,47	0,5	PET	50 µ
Silver 70 C	1%	44%	44%	44%	68%	64%	43%	35%	22%	64%	0,31	5,16	0,36	PET	50 µ
Silver 80 C	1%	23%	60%	58%	80%	75%	55%	33%	12%	80%	0,2	5,1	0,2	PET	50 µ
Silver 95 C	<1%	5%	60%	60%	87%	83%	62%	33%	4%	96%	0,09	5,1	0,1	PET	60 µ
Silver 99 C	<1%	0,5%	82%	82%	91%	88%	78%	18%	4%	96%	0,09	5,1	0,1	PET	60 µ
Steel 50 C	1%	49%	14%	12%	42%	40%	13%	43%	44%	46%	0,59	5,7	0,6	PET	60 µ
Steel 65 C	1%	43%	17%	14%	50%	48%	16%	46%	38%	51%	0,5	5,65	0,5	PET	60 µ
Steel 75 C	1%	30%	25%	20%	61%	58%	23%	51%	26%	65%	0,39	5,65	0,4	PET	50 µ
Vista 80 C	1%	20%	43%	19%	76%	73%	50%	38%	12%	80%	0,25	5,1	0,28	PET	50 µ
Vista 90 C	1%	10%	63%	18%	82%	78%	57%	34%	9%	90%	0,18	5,1	0,2	PET	50 µ
Anti-UV															
Clear 1 UVC	0,5%	90%	9%	9%	14%	15%	9%	7%	84%	13%	0,85	-	0,9	PET	50 µ
Natural 40 UVC	0,5%	66%	11%	11%	42%	40%	18%	26%	56%	28%	0,59	5,8	0,7	PET	50 µ

(*on double glazing 4-16-4)