

INVÄNDIGA SOLSKYDDSFILMER

| Filmtyp | UV transmission | Visible light transmission | Reflection of external visible light | Reflection of internal visible light | Total solar energy rejected | Total solar energy rejected * | Solar energy reflection | Solar energy absorption | Solar energy transmission | Reduction in Solar Glare | G-value | U-value | Shading coefficient | Film composition | Thickness |
|------------------------|-----------------|----------------------------|--------------------------------------|--------------------------------------|-----------------------------|-------------------------------|-------------------------|-------------------------|---------------------------|--------------------------|---------|---------|---------------------|------------------|-----------|
| Solskyddsfilmer | | | | | | | | | | | | | | | |
| 3M Prestige 40 INT | 0,1% | 40% | 7% | 7% | 60% | 48% | - | - | - | 38% | 0,41 | - | 1,0 | PET | 50 µ |
| 3M Prestige 70 INT | 0,1% | 69% | 9% | 9% | 50% | 44% | - | - | - | 50% | 0,50 | - | 1,4 | PET | 50 µ |
| Blue 10 INT | 1% | 12% | 18% | 63% | 72% | 68% | 35% | 47% | 18% | 86% | 0,27 | 5,13 | 0,3 | PET | 50 µ |
| Bronze 10 INT | 1% | 12% | 18% | 55% | 76% | 72% | 34% | 57% | 9% | 91% | 0,23 | 5,1 | 0,2 | PET | 50 µ |
| Copper 20 INT | 1% | 20% | 36% | 36% | 77% | 72% | 45% | 42% | 13% | 79% | 0,22 | 5,1 | 0,2 | PET | 60 µ |
| Copper 35 INT | 1% | 35% | 26% | 26% | 65% | 60% | 39% | 36% | 25% | 63% | 0,34 | 5,23 | 0,39 | PET | 60 µ |
| Copper 50 INT | 1% | 50% | 17% | 17% | 55% | 50% | 22% | 43% | 35% | 50% | 0,46 | 5,39 | 0,5 | PET | 60 µ |
| Gold 15 INT | 1% | 15% | 50% | 64% | 78% | 75% | 50% | 38% | 8% | 83% | 0,25 | 5,1 | 0,28 | PET | 50 µ |
| Green 15 INT | 1% | 15% | 36% | 63% | 77% | 73% | 36% | 55% | 9% | 85% | 0,23 | 5,1 | 0,2 | PET | 50 µ |
| Multiglass 50 INT | 1% | 47% | 29% | 28% | 66% | 63% | 47% | 25% | 28% | 52% | 0,36 | 4,9 | 0,4 | PET | 55 µ |
| Prisma 65 INT | 1% | 68% | 18% | 15% | 59% | 55% | 27% | 36% | 37% | 29% | 0,41 | 4,9 | 0,4 | PET | 55 µ |
| Prisma 70 INT | 1% | 70% | 7% | 7% | 49% | 45% | 27% | 26% | 47% | 30% | 0,49 | 4,9 | 0,5 | PET | 55 µ |
| Secret 10 INT | 1% | 10% | 63% | 18% | 82% | 78% | 57% | 34% | 9% | 90% | 0,18 | 5,1 | 0,2 | PET | 50 µ |
| Secret 20 INT | 1% | 20% | 43% | 19% | 76% | 73% | 50% | 38% | 12% | 80% | 0,25 | 5,1 | 0,28 | PET | 50 µ |
| Silver 01 INT | <1% | 0,5% | 82% | 82% | 91% | 88% | 78% | 18% | 4% | 96% | 0,09 | 5,1 | 0,1 | PET | 60 µ |
| Silver 05 INT | <1% | 5% | 60% | 60% | 87% | 83% | 62% | 33% | 4% | 96% | 0,09 | 5,1 | 0,1 | PET | 60 µ |
| Silver 25 INT | 1% | 23% | 60% | 58% | 80% | 75% | 55% | 33% | 12% | 80% | 0,2 | 5,1 | 0,2 | PET | 50 µ |
| Silver 45 INT | 1% | 44% | 44% | 44% | 68% | 64% | 43% | 35% | 22% | 64% | 0,31 | 5,16 | 0,36 | PET | 50 µ |
| Silver 60 INT | 1% | 59% | 26% | 26% | 58% | 54% | 31% | 29% | 40% | 47% | 0,45 | 5,47 | 0,5 | PET | 50 µ |
| Steel 30 INT | 1% | 30% | 25% | 20% | 61% | 58% | 23% | 51% | 26% | 65% | 0,39 | 5,65 | 0,4 | PET | 50 µ |
| Steel 45 INT | 1% | 43% | 17% | 14% | 50% | 48% | 16% | 46% | 38% | 51% | 0,5 | 5,65 | 0,5 | PET | 60 µ |
| Steel 50 INT | 1% | 49% | 14% | 12% | 42% | 40% | 13% | 43% | 44% | 46% | 0,59 | 5,7 | 0,6 | PET | 60 µ |
| Anti-UV | | | | | | | | | | | | | | | |
| Clear 1 UV INT | 0,5% | 90% | 9% | 9% | 14% | 15% | 9% | 7% | 84% | 13% | 0,85 | NC | 0,9 | PET | 50 µ |
| Neutral 40 UV INT | 0,5% | 66% | 11% | 11% | 42% | 40% | 18% | 26% | 56% | 28% | 0,59 | 5,8 | 0,7 | PET | 50 µ |

* on double glazing 4-16-4