



### STEEL 75 C

Steel 75 C films are highly effective at reducing solar heat gain, whilst at the same time continuing to allow some natural light transmission. They help noticeably reduce solar glare, conveying a touch of colour and customization to the external aspect of a building.



SOLAR SCREEN® Warranty  
**10 YEARS**



Fire-resistance rating  
**M1**



Storage from -5°C to +40°C  
**3 YEARS**



REACH RoHS compliant  
**RESPECTED**

### WIDTHS AVAILABLE:

↔ **152 cm**

↔ **183 cm**

### TECHNICAL DATASHEET


Data calculated based on film applied to clear glass 3 mm thick (\*on double glazing 4-16-4)

Ultraviolet transmission	1 %
Visible light transmission	30 %
Reflection of external visible light	25 %
Reflection of internal visible light	20 %
Total solar energy rejected	61 %
Total solar energy rejected 2*	58 %
Solar ratio :	
Solar energy reflection	23 %
Solar energy absorption	51 %
Solar energy transmission	26 %
Reduction in Solar Glare	65 %
g-value	0.39
u-value	5.65
Shading coefficient	0.4
Installation type : Interior	
Roll length	30,5 m
Film composition	PET
Thickness	50 µ

Colour from the outside : NEUTRAL

### CONSTRUCTION

1. "Hard" scratch resistant layer, for durability and ease of maintenance during window cleaning
2. Dyed polyester without optical distortion, with anti IR metal particles deposit
3. Bonding adhesive
4. Dyed polyester without optical distortion
5. PS adhesive, glass polymerization within 15 days
6. Protection release liner, disposable after installation



### INSTALLATION ADVICE

Vertical installation and on standard glass surface\*\*

Clear single pane	✓
Tinted single pane	!
Reflective tinted single pane	✓
Clear double pane	✗
Tinted double pane	✗
Reflective tinted double pane	✓
Gas-filled double pane - Low E	✗
STADIP EXT. clear double pane	✗
STADIP INT. clear double pane	✗

✓ Yes    ! Caution    ✗ Not recommended

\*Recommendations provided on the basis of a glazed surface covering up to 2.5m<sup>2</sup>, contact us for definitive details or to obtain a thermal shock analysis report.

### MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. 0805 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

*Non-contractual data, SOLAR SCREEN® reserves the right to modify the composition of its films at any time. Consult our guarantee vouchers and our general conditions of sale.*