



CU 20 DB36 - ANTI-HIGH FREQUENCY FILM

The CU 20 dB36 - Anti-high frequency film considerably reduces solar heat while retaining some of the natural light. It allows a good reduction of glare and brings to the building a colored and personalized touch. Finally, thanks to its pure copper alloy, it effectively protects high frequencies and attenuates up to almost 37 dB.



TECHNICAL DATA

Data calculated based on film applied to clear glass 3 mm thick (* on double glazing 4-16-4)

Ultraviolet transmission	1%
Visible light transmission	21%
Reflection of external visible light	37%
Reflection of internal visible light	37%
Total solar energy rejected	80%
Total solar energy rejected 2 *	86%
Solar ratio:	
Solar energy reflection	47%
Solar energy absorption	39%
Solar energy transmission	14%
Reduction in Solar Glare	80%
G-value	0.27
U-value	NC
Shading coefficient	0.2
Installation type	Exterior
Roll length	30,5 m
Film composition	PET
Thickness	110 µ
Colour from the outside	Copper

MAINTENANCE

Use soapy water solution for cleaning. Do not clean for at least a month after installation and do not apply any type of stickers or adhesive on the film. For more information read our maintenance instructions and quality standards on our website, www.solfilm.se

INSTALLATION ADVICE

Vertical installation and on standard glass surface *


Clear single pane	✓
Tinted single pane	✓
Reflective tinted single pane	✓
Clear double pane	✓
Tinted double pane	✓
Reflective tinted double pane	✓
Gas-filled double pane - Low E	!
STADIP EXT. clear double pane	✗
STADIP INT. clear double pane	!

✓ Yes ! Caution ✗ Not

Recommended
* Recommendations provided on the basis of a glazed surface covering up to 2.5 m², contact us for definitive details or to obtain a thermal check analysis report.

CONSTRUCTION

1. Hard scratch resistant layer, for durability and ease of maintenance during window cleaning
2. High optical quality polyester, with anti IR metal particles deposition
3. Bonding adhesive
4. High optical quality polyester
5. PS adhesive, glass polymerization within 15 days
6. Protection release liner, disposable after installation



Fire-resistance rating



Storage from -5°C to +40°C
3 YEARS



REACH RoHS compliant
RESPECTED